

TECHNICAL INFORMATION

Sunshine

Resistant onglaze colors for bone china, vitreous china, earthenware and porcelain

Lead content

Ref. No.	Assortment	Pb-content %
11 1232	105	29
11 1233	105	31
11 1234	105	26
11 1235	105	25
12 1232	105	32
12 1234	105	26
13 1230	105	26
13 1232	105	32
13 1233	105	33
14 1231	105	31
14 1232	105	24
15 1230	105	32
16 1232	105	40

Ref. No.	Assortment	Pb-content %
16 1233	105	39
17 578	105	52
17 1230	105	26
17 1231	105	25
17 1232	105	25
17 1233	105	44
19 1230	105	24
19 1231	105	23
19 1232	105	36
72 1233	105	33
77 1234	105	44
77 1235	105	44
77 1239	105	31

The specified lead contents are theoretical values that have been rounded off to give whole numbers, i.e. values which have been calculated from the formulas and which may vary from the actual (analytical) values as a result of production or the fact that they have been rounded off. Due to the time and costs involved we are not able to analyze every single batch separately. Comparisons of the theoretical and analytical values of selected samples have shown, however, that the calculated contents are sufficiently accurate. In isolated cases the extent to which the calculated values were exceeded absolutely was 1 %.

The theoretical lead contents provided here voluntarily do not represent any binding product properties in terms of application specifications and will be revised by us when new knowledge on the composition of products is available.